



Product Data Sheet



Product Name: **Complēt® LGF20-PP**

Resin Description: **Homopolymer Polypropylene (PP)**

Fiber Type: **Long Glass Fiber**

Fiber Content (weight percent): **20%**

	English	SI	Test Method
Specific Gravity	1.03	1.03	ASTM D-792
Tensile Strength	14,500 psi	100 MPa	ASTM D-638
Tensile Modulus	630 ksi	4345 MPa	ASTM D-638
Tensile Elongation	3-4 %	3-4 %	ASTM D-638
Flexural Strength	21,000 psi	145 MPa	ASTM D-790
Flexural Modulus	630 ksi	4345 MPa	ASTM D-790
Notched Izod Impact	4.0 ft-lb/in	214 J/m	ASTM D-256
Un-notched Izod Impact	13.0 ft-lb/in	694 J/m	ASTM D-4812
DTUL @ 264 psi (1820 kPa)	295 °F	146 °C	ASTM D-648

Rev 07/14

Molding guidelines and processing conditions for Complēt long fiber composite pellets are available in our Material Processing Guide. Please contact our technical support team if you require additional information regarding processing a particular product or guidance resolving problems.

This compound complies with European Union Directive 2002/95/EC Restriction of Hazardous Substances (RoHS).

Values included in this Property Data Sheet are based on limited laboratory test specimens. These values are typical values and are not meant to be used for setting maximum or minimum values for specification purposes. Any determination of the suitability of the materials shown in this property data sheet for use by the end user is the sole responsibility of the user, who must assure themselves that the material as subsequently processed meets the need of his particular product or use. To the best of our knowledge the information in this publication is accurate and reliable, PlastiComp does not assume any liability whatsoever for the accuracy of this information.