



## Product Data Sheet



Product Name: **Velocity® LCF50-PA66**

Resin Description: **High Flow Nylon 66 (Polyamide 66)**

Fiber Type: **Long Carbon Fiber**

Fiber Content (weight percent): **50%**

	English	SI	Test Method
<b>Specific Gravity</b>	1.37	1.37	ASTM D-792
<b>Tensile Strength</b>	45,000 psi	310 MPa	ASTM D-638
<b>Tensile Modulus</b>	5,800 ksi	40000 MPa	ASTM D-638
<b>Tensile Elongation</b>	1 %	1 %	ASTM D-638
<b>Flexural Strength</b>	72,000 psi	497 MPa	ASTM D-790
<b>Flexural Modulus</b>	4,250 ksi	29310 MPa	ASTM D-790
<b>Notched Izod Impact</b>	3.4 ft-lb/in	182 J/m	ASTM D-256
<b>Un-notched Izod Impact</b>	13.5 ft-lb/in	721 J/m	ASTM D-4812
<b>DTUL @ 264 psi (1820 kPa)</b>	485 °F	252 °C	ASTM D-648

Rev 12/14

Molding guidelines and processing conditions for Complēt long fiber composite pellets are available in our Material Processing Guide. Please contact our technical support team if you require additional information regarding processing a particular product or guidance resolving problems.

This compound complies with European Union Directive 2002/95/EC Restriction of Hazardous Substances (RoHS).

Values included in this Property Data Sheet are based on limited laboratory test specimens. These values are typical values and are not meant to be used for setting maximum or minimum values for specification purposes. Any determination of the suitability of the materials shown in this property data sheet for use by the end user is the sole responsibility of the user, who must assure themselves that the material as subsequently processed meets the need of his particular product or use. To the best of our knowledge the information in this publication is accurate and reliable, PlastiComp does not assume any liability whatsoever for the accuracy of this information.

PlastiComp, Inc. • 110 Galewski Drive • Winona, Minnesota, 55987 U.S.A.  
Telephone 1-507-454-4334 • Fax 1-507-452-5642 • Internet [www.plasticomp.com](http://www.plasticomp.com) • Email [info@plasticomp.com](mailto:info@plasticomp.com)